

Vincerit, Stephen C.

Attorney Docket No. P04860US1

Amendments To the Claims

Claims 1-6 (Canceled)

Claim 7 (Currently Amended): A thin film chip resistor comprising:
a substrate;
a single metal thin film resistive layer directly attached to the substrate, the metal thin film layer
being non-tantalum;
a chip resistor termination attached on each end of the metal thin film resistive layer; and
an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the
metal thin film resistive layer for reducing failures due to electrolytic corrosion under
powered moisture conditions; and
the outer moisture barrier formed from deposition of tantalum oxide and not through oxidation of
tantalum.

Claim 8 (Original): The thin film resistor of claim 7 wherein the metal film layer is an alloy
containing nickel.

Claim 9 (Original): The thin film resistor of claim 7 wherein the metal film layer is an alloy
containing chromium.

Claim 10 (Original): The thin film resistor of claim 7 wherein the metal film layer is a nickel-
chromium alloy.

Vincent, Stephen C.

Attorney Docket No. P04860US1

Claim 11 (Canceled)

Claim 12 (Original): The thin film resistor of claim 7 wherein the tantalum pentoxide layer is overlaid by sputtering.

Claim 13 (Currently Amended): A nickel-chromium alloy thin film chip resistor comprising:
an alumina substrate;
a single nickel-chromium alloy thin film layer directly contacting the substrate;
a chip resistor termination attached on each end of the nickel-chromium alloy thin film; and
an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the
nickel-chromium alloy thin film layer for reducing failures due to electrolytic corrosion
under powered moisture conditions; and
the outer moisture barrier formed from deposition of tantalum oxide and not through oxidation of
tantalum.

Claim 14 (Canceled)

Claim 15 (Currently amended): A nickel-chromium alloy thin film chip resistor comprising:
an alumina substrate;
a single nickel-chromium alloy thin film layer directly contacting the substrate;
a chip resistor termination attached on each end of the nickel-chromium alloy ~~thin~~ thin film;
a passivation layer directly overlaying and contacting the nickel-chromium alloy layer; and

Vincent, Stephen C.

Attorney Docket No. P04860US1

an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the passivation layer for reducing failures due to electrolytic corrosion under powered moisture conditions; and
the outer moisture barrier formed from deposition of tantalum oxide and not through oxidation of tantalum.

Claim 16 (Canceled)